

BITUTAK^{MB} SMOOTH



PRODUCT DESCRIPTION

- ▶ DERBIGUM proven performance at an exceptional value.
- ▶ Manufactured from a unique blend of APP (atactic polypropylene) polymers and select asphalts that enhances the weathering capabilities and UV resistance of the membrane.
- ▶ Reinforced with a heat resistant non-woven polyester mat which provides the strength and durability necessary in a roofing membrane.
- ▶ Adapts well to the use of aluminum or other fine coatings.
- ▶ Membranes are film-backed for ease of heat-welding installation.

TECHNICAL CHARACTERISTICS

BITUTAK^{MB} Smooth Results*
ASTM Test Methods D6222-16

CHARACTERISTIC	TESTED	MACHINE DIRECTION	CROSS DIRECTION	UNITS
Tensile Strength	0°F	90	65	lbf/in
	77°F	80	60	lbf/in
Elongation	0°F	20	20	%
	77°F	55	70	%
Tear Resistance	77°F	100	80	lbf
Dimensional Stability		0	0	%

CHARACTERISTIC	INITIAL	AGED	UNITS
Cold Flex	-18	-2	°C

Tested initially within 24 hours and again aged 28 days.

CHARACTERISTIC	MINIMUM	UNITS
Compound Stability	Pass	

* All values shown are nominal and subject to normal manufacturing tolerances.

PRODUCT INFORMATION

CHARACTERISTIC	US CUSTOMARY	METRIC
Thickness	152 mils	3.9 mm
Length	33 ft 6 in	10.2 m
Width	39 3/8 in	1.0 m
Weight	88 lb	39.9 kg
Net Coverage	100 sq ft	9.2 sq m

FIRE SAFETY GUIDELINES

NOTE: Torch application of BITUTAK^{MB} Smooth may pose a threat of fire if strict application standards and procedures are not followed. All operators of torch equipment should be thoroughly trained. In addition a fire watch should be maintained on the project for not less than 60 minutes following the last heat welded work of the day. An ABC approved fire extinguisher should be on the site for each torch in operation.

PACKAGING & STORAGE

Packaged 20 rolls per pallet. Rolls should be stored on end, on raised platforms protected from the weather.

SDS available
on request:
(800) 727-9872
www.bitutak.com

