

CORETECT¹⁹

Wet/Dry Ultra Rubberized Flashing Cement

DESCRIPTION

CoreTect 19 Flashing Cement is an asbestos-free professional-grade blend of specially processed asphalt, functional fillers, fibers, thermoplastic elastomers and petroleum solvents that, when properly applied, cure to form a durable, pliable seal or adhesive on a variety of roofing substrates. CoreTect's highly thixotropic nature makes it easy to apply on parapet walls and flashings without slumping or sagging. Product is available in a summer, semi and winter grade.

USES

CoreTect 19 Flashing Cement can be used to seal and repair minor cracks, blisters and fissures in asphalt roofing membranes, BUR systems and asphalt shingles. It also makes an excellent sealant for flashing around gutters, vents, pitch pans, skylights and chimneys, exhibiting excellent adhesion to metal, brick, masonry and aluminum substrates.

APPLICATION

All surfaces should be clean, dry and free from oil, grease, dust, dirt, loose paint or other foreign matter. Excess water should be removed, if possible, before application.

CoreTect 19 is ready to be applied out of the can by trowel or a gloved-hand to clean dry, wet or damp substrates; can even be applied under ponding water. Store product at less than 70°F for 24 hours prior to application when ambient temperature is less than 50°F. DO NOT THIN material with additional solvent or fuel.

Apply material into cracks and openings, feathering the edges, at 1/8 – 1/4 inch thick. On larger openings, first apply a layer of CoreTect 19, working the material into the opening, then apply a reinforcing fabric to cover and exceed the length and width of the opening, followed by a second application of flashing cement; feather the edges 4 inches beyond the width of the fabric. Do not apply to coal tar roofs or EPDM membranes. Do not use to fill pitch pans with voids greater than 1/4 inch.

PRODUCT INFORMATION

CHARACTERISTIC	U.S. CUSTOMARY	TEST METHOD
Flash Point	<104	ASTM D93
Viscosity, cps	125,000 - 200,000	Encore DSR
Sag @ 160	Pass	ASTM D4586
Pliability @ 32	Pass	ASTM D4586
Density (Water = 1)	1.13	ASTM D6511
VOC Content, grams/Liter	<250	ASTM D3930

PACKAGING & STORAGE

CoreTect 19 is available in the following containers sizes:

- 1 gallon pail (3.8 L)
- 3 gallon pail (11.4 L)
- 5 gallon pail (18.9 L)

Store in a well-ventilated area far away from any heat source.



SDS available
on request:
(800) 727-9872
www.derbigum.us